

ARMY RESEARCH LABORATORY



On Theories of the Grüneisen Parameter

by Steven B. Segletes
and William P. Walters

ARL-TR-1303

March 1997

UNCLASSIFIED

Approved for public release; distribution is unlimited.

19970224 127

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer need. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5066

ARL-TR-1303**March 1997**

On Theories of the Grüneisen Parameter

Steven B. Segletes, William P. Walters
Weapons and Materials Research Directorate, ARL

Abstract

A recently proposed equation of state is further examined for compatibility with prior theory. It is found, by adopting a more realistic functional relationship for one of the thermodynamic state variables and eliminating higher-order terms from the model, that three historical theories for determination of the Grüneisen function fall directly out of the recently proposed model. One is led to conclude that the newer model captures the essence of all of the older theories, each of which being applicable under an appropriate circumstance.

TABLE OF CONTENTS

	<u>Page</u>
LIST OF FIGURES	v
1. BACKGROUND	1
2. THE HIGH-COMPRESSION LIMIT FOR $\psi(V)$	6
3. A POWER LAW FOR $\psi(V)$	8
4. GRÜNEISEN MODELS	12
5. NONIDEAL EFFECTS	16
6. CONCLUSIONS	22
7. REFERENCES	25
DISTRIBUTION LIST	27
REPORT DOCUMENTATION PAGE	43

INTENTIONALLY LEFT BLANK

LIST OF FIGURES

<u>Figure</u>	<u>Page</u>
1. Limiting ψ values for several metals (solid lines), obtained by inserting TFD cold-curve values into equation of state of Segletes. Superimposed (dashed lines) are limiting ψ values associated with the linear ψ assumption.	7
2. Limiting ψ values for several metals (solid lines), obtained by inserting TFD cold-curve values into equation of state of Segletes. Superimposed (dashed lines) are limiting ψ values associated with the power-law $\psi(V)$ assumption.	9
3. Lattice binding energy as a function of nondimensionalized lattice spacing for a material. Dark line is UCC model of Rose <i>et al.</i> [10]. Dashed lines are for model of Segletes [15,16], with linear ψ assumption, for two particular values of $\Gamma_0 \psi'$ and an anharmonicity of 3.	11
4. Lattice binding energy as a function of nondimensionalized lattice spacing for a material. Dark line is UCC model of Rose <i>et al.</i> [10]. Dashed lines (essentially coincident) are for model of Segletes [15,16], with power-law $\psi(V)$ assumption, for anharmonicity values of 2, 4, 6, 8, and 10.	13
5. Grüneisen function versus relative volume for hypothetical material with $\Gamma_0=2$ and $K=1$, using power-law $\psi(V)$, with $x=4/9$. Predictions using models of Slater [4], Dugdale and MacDonald [5], and the free-volume theory [6] are shown for comparison. Note that ambient value associated with power-law $\psi(V)$ matches that of Slater.	17

LIST OF FIGURES (CONTINUED)

<u>Figure</u>	<u>Page</u>
6. Grüneisen function versus relative volume for hypothetical material with $\Gamma_0=2$ and $K=1$, using power-law $\psi(V)$, with $x=2/3$. Predictions using models of Slater [4], Dugdale and MacDonald [5], and the free-volume theory [6] are shown for comparison. Note that ambient value associated with power-law $\psi(V)$ matches that of Dugdale and MacDonald.	17
7. Grüneisen function versus relative volume for hypothetical material with $\Gamma_0=2$ and $K=1$, using power-law $\psi(V)$, with $x=8/9$. Predictions using models of Slater [4], Dugdale and MacDonald [5], and the free-volume theory [6] are shown for comparison. Note that ambient value associated with power-law $\psi(V)$ matches that of the free-volume theory.	18
8. Pressure-volume curves for stainless steel. Cold data to 4 Mbar shown with filled symbols. Hugoniot data to 2 Mbar shown with open symbols. Curves represent cold-compression and shock-Hugoniot curves with $\Gamma=1.81$ and power-law $\psi(V)$ exponent x , equal to 0.72.	20
9. Grüneisen function versus relative volume for stainless steel with $\Gamma_0=1.81$, using power-law $\psi(V)$, with $x=0.72$. Predictions using models of Slater [4], Dugdale and MacDonald [5], and the free-volume theory [6] are shown for comparison. .	20

1. BACKGROUND

The estimation and measurement of the Grüneisen function for metals is an important but difficult task. Simple formulas exist for its estimation, in terms of specific heat and compressibility, or alternately in terms of derivatives of the cold (*i.e.*, zero degree) compression curve, or still again in terms of derivatives of the lattice frequency. Depending on the validity of various assumptions about the material, some of these definitions may be redundant. However, when applied to actual substances, these methods can produce estimates that vary by significant amounts (100%, in some cases [1]), even at ambient conditions.

Some variation is due to the fact that the Grüneisen assumption, which has the Grüneisen function independent of temperature, is only an approximation. It is well known [2,3], for example, that at low temperatures (at fractions of the Debye temperature) the Grüneisen parameter is indeed temperature dependent. Grodzka [1] presents data showing a significant thermal variation in the Grüneisen parameter at higher temperatures as well, for some materials. Other variations in the estimate arise out of the differences in modeling of the propagation velocities associated with lattice vibration. Three widely referenced models of this variety, which provide not only an ambient value but also a volume-dependent estimate of the Grüneisen function, are those of Slater [4], Dugdale and MacDonald [5], and the free-volume theory [6]. Pastine [7] and Vashchenko and Zubarev [6] have attempted to generalize results by showing that the variation of Poisson's ratio with volume can account for some of the differences in the various models of the Grüneisen parameter. Unfortunately, experimental knowledge of how Poisson's ratio varies with compression and/or temperature is as elusive as knowledge of the Grüneisen function itself.

Historically, the estimation of the Grüneisen function was further complicated by the paucity of cold-compression data. Available high-pressure data were almost exclusively that of shock transition, and so the cold-compression curves, needed by the various models in order to estimate the Grüneisen function, were necessarily back-extrapolated from shock data using a Grüneisen function that was *a priori* unknown (*e.g.*, see Walsh *et al.* [8]).

To some extent, this uncertainty in the functional behavior of the Grüneisen function has persisted to the present. For example, Segletes [9] examined the Grüneisen formulations present in five of the widely used hydrocodes, which were developed by the U.S. Department of Energy (DOE) national labs and the U.S. Department of Defense (DOD), as well as industry. In examining these codes, which are utilized to model the high-compression deformations associated with high-velocity impact and/or explosive loading, it was noted that a common Grüneisen formulation was not employed. Not only were the Grüneisen formulations different from code to code, but Segletes was able to show, in some cases, that thermodynamic instabilities would result because of an incompatible selection of Grüneisen and Hugoniot functions.

In a significant work, which, on the surface, might not appear to shed light on the problem of estimating the Grüneisen function, Rose *et al.* [10] proposed (in 1984) a universal cold curve, which was able to provide a generic function for the lattice binding energy, which could be appropriately scaled to match theoretical and experimental data for many metals. Since the work of Rose and his colleagues, others have continued in the area as well, notably the same team led by Vinet [11,12] and, more recently, a group led by Baonza [13,14]. These later efforts succeeded in introducing temperature effects and thus produced a Grüneisen-style equation of state. However, in all of these more recent efforts cited, the function governing the reference-compression curve was mutually exclusive of the function used to model the thermal effects. In the works of Vinet *et al.*, the variation of the bulk modulus was fitted for a number of materials, which effectively parlayed into a Grüneisen function. In the case of Baonza *et al.*, a particular, commonly employed, functional form of the Grüneisen function was used—namely, Γ/V equals a fitted constant. While all of these works are worthy efforts in their own right, their primary contribution lies in an area other than the theory of the Grüneisen function.

Segletes [15,16] recently proposed an equation of state for metals, which captures, in the absence of phase change, the behavior of metals into the megabar range. The model was likewise inspired by the universal cold-curve work of Rose *et al.* [10]. However, unlike the efforts of Vinet *et al.* [11,12] and Baonza *et al.* [13,14], in which the function governing the cold compression was mutually exclusive of the function used to model the thermal effects, the recent

work of Segletes, by expressing the binding-energy function in terms of lattice frequency, as opposed to lattice compression, unified the functions governing cold-compression and thermal effects. In essence, a specification of the cold-compression behavior in Segletes' model automatically yields the Grüneisen function, and conversely, a specification of the thermal effects, by way of the Grüneisen function, automatically yields a cold-compression curve.

Segletes' equation is of the Grüneisen variety and is given by

$$p\psi - E = E_b \left\{ \left[(\Theta/\Theta_0)^K - 1 \right] + K(K-1) (\Theta/\Theta_0)^K \ln(\Theta/\Theta_0) \right\} , \quad (1)$$

where p and E are the pressure and specific internal energy, respectively, and the constant E_b is the specific binding energy of the lattice. The terms Θ_0 and Θ are the ambient and current values of the characteristic temperature of the lattice, which, according to the tenets of Grüneisen theory, is assumed to be a function of volume only and is proportional to the maximum lattice vibrational frequency, ν . The concepts of characteristic temperature and lattice frequency derive from the early work on specific heats at low temperatures, by Einstein, Debye, Born and von Karman, and others. In the current context, the characteristic temperature serves as a macroscopic parameter that permits the vibrational frequency of the lattice (a microscopic quantity) to be inferred—namely, the theory of specific heats has these two parameters directly proportional. Returning to eqn. (1), the parameter ψ is the thermodynamic state variable equal to the ratio of specific volume to the Grüneisen parameter, V/Γ , introduced by Segletes [17,18] for convenience in manipulating the thermodynamic equations. The constant K is given by

$$K = \frac{C_0}{\Gamma_0 \sqrt{E_b}} , \quad (2)$$

which incidentally is $1/(3\Gamma_0)$ times the anharmonicity of the lattice. Values for K have been observed to cluster in the $2/3$ to $4/3$ range for metals, which is compatible with the model's

behavior becoming greatly idealized (*i.e.*, linear in Θ/Θ_0) when the constant K takes on a value of unity. C_0 is the bulk sound speed at absolute zero temperature and pressure, and Γ_0 is the ambient value of the Grüneisen parameter.

In this model, the cold curve (*i.e.*, zero-degree isotherm) is given by

$$E_c = E_b \left\{ 1 - [1 - K \ln(\Theta/\Theta_0)] (\Theta/\Theta_0)^K \right\} \quad (3)$$

and

$$p_c = \frac{E_b K^2}{\psi} (\Theta/\Theta_0)^K \ln(\Theta/\Theta_0) , \quad (4)$$

where p_c and E_c are the cold pressure and specific cold energy, respectively.

In macroscopic terms, the Grüneisen function, Γ , is defined by $\Gamma = V/\psi = V(\partial p/\partial E)_v$. From microscopic arguments, however, the characteristic temperature, Θ (alternately, the maximum lattice vibrational frequency, ν), is related to the ψ variable through the relationship that defines the Grüneisen parameter:

$$\frac{\nu'}{\nu} = \frac{\Theta'}{\Theta} = -\frac{1}{\psi} , \quad (5)$$

where primes (here and throughout the paper) denote ordinary differentiation with respect to specific volume. In the general case, the differentiation in eqn. (5) would be partial at constant temperature. However, for Grüneisen materials, in which $\Gamma = \Gamma(V)$ only, the derivative in eqn. (5) becomes ordinary.

It is interesting to note the distinction between Segletes' equations and those of an ideal, harmonic oscillator, which is often used to approximate a crystal lattice for purposes of theoretical derivation. In the case of Planck's harmonic oscillator at zero temperature [19], dE_c/dv is constant. No lattice is truly harmonic, of course, or else its thermal expansion coefficient and Grüneisen function would both be identically zero. From eqns. (3) and (5), it can be seen, for the idealized case where K is unity, that the current model would have $dE_c/dv \propto \ln(v/v_0)$. A theoretical explanation for this distinction is not yet postulated.

Once the ψ function is defined, integration of eqn. (5) gives the characteristic temperature, which is the primary equation-of-state variable in eqn. (1). In the original papers, Segletes [15,16] incorporated a linear relationship for $\psi(V)$, based on results of his prior work on thermodynamic stability [9,17,18], given in general form by

$$\psi/\psi_0 = 1 - (\Gamma_0\psi')(1 - V/V_0) \quad . \quad (6)$$

The ambient values of specific volume and Grüneisen parameter determine ψ_0 , while the constant $(\Gamma_0\psi')$ was the sole material parameter that was actually fitted to the cold curve of each metal. The fitted values of $(\Gamma_0\psi')$, for nine metals, ranged from 0.43 to 0.88, with a vast majority clustered in the vicinity of 0.8. In terms of compression, μ , equal to $(V_0 - V)/V$, the linear ψ translates to a Grüneisen function of the form $\Gamma = \Gamma_0/(1 + \beta\mu)$, with β as the fitting parameter.

This assumed linear relationship produced an excellent match to empirical data and first-principles computations over a very wide range of specific volumes. However, for extremely large compressions, this linear relationship can no longer be expected to hold, as it is later shown that the ψ variable must vanish in the high-compression limit ($V \rightarrow 0$), whereas the linear form of eqn. (6) will not do so for values of $(\Gamma_0\psi')$ other than unity.

In this report, a power law for the $\psi(V)$ parameter, to replace the linear relationship originally employed, is adopted. Though this choice of function still suffers deficiencies at very large compressions, a number of positive outcomes result in the context of Segletes' model [15,16] with this change: 1) the $\psi(V)$ parameter vanishes with diminishing specific volume, as is required; 2) binding-energy expansion data for actual metals are better fit with the power law, as compared to the linear assumption; and most importantly, 3) Segletes' equation of state is shown, by neglecting higher-order terms, to reduce to the model of Slater [4], or Dugdale and MacDonald [5], or to the free-volume theory [6], depending on the value of the exponent used in the power law for $\psi(V)$.

2. THE HIGH-COMPRESSION LIMIT FOR $\psi(V)$

With the linear relation for $\psi(V)$, given by eqn. (6), the high-compression limit for ψ approaches a value of $\psi_0 (1 - \Gamma_0 \psi')$, which would typically lie in the $0.2 \cdot \psi_0$ range for metals. To show what high-pressure limit is appropriate for ψ , in the context of the new model, theoretical values for cold pressure and energy using Thomas-Fermi-Dirac (TFD) theory for several metals were inserted into the new model in order to back out values for ψ . In this manner, the high-pressure limiting functional behavior for ψ , which would be required to match TFD theory, was obtained. Values for the TFD data were obtained using the analytical fitting equations described by Kerley [20].

It is not asserted here that the new equation of state can or should capture the high-compression atomic interactions modeled with TFD zero-temperature theory. Rather, it merely makes sense, from an application point of view, that the current model should blend smoothly into TFD theory, so that a computational implementation can smoothly transition between applicable theories.

Results of the TFD fits for ψ are shown in Figure 1, for several metals. Superimposed on the graph are lines of constant $\Gamma_0 \psi'$, which characterized the original linear form employed by Segletes [15,16]. A finite limiting value of ψ implies that Γ approaches zero in the high-




Figure 1. Limiting ψ values for several metals (solid lines), obtained by inserting TFD cold-curve values into equation of state of Segletes. Superimposed (dashed lines) are limiting ψ values associated with the linear ψ assumption.

compression limit, which is known not to be the case. The TFD results indicate that ψ must drop to zero with decreasing specific volume, which indicates that the limiting value of Γ is nonzero, but instead related to the limiting slope. Regardless of material, the TFD results are roughly linear, having a slope of approximately 2 in the very-low-volume limit, with the slope diminishing slightly with increasing volume. A finite limiting slope of value m in Figure 1 implies a limiting value of the Grüneisen parameter of Γ_0/m . The fact that (in the case of $m \approx 2$) $\Gamma_0/2$ doesn't equal 1/2 or 2/3, as might be expected, merely indicates that the current model fails to capture the essence of TFD theory, which is no great surprise since the model's equations are not those of TFD theory. In any event, the linear treatment of ψ , originally employed, does not blend smoothly into the realm where TFD theory governs. Another functional choice for ψ might be more appropriate.

3. A POWER LAW FOR $\psi(V)$

As an alternative to the linear relationship for $\psi(V)$, given by eqn. (6), a power law of the form

$$\psi/\psi_0 = (V/V_0)^x \quad (7)$$

is investigated. The power-law form for $\psi(V)$ retains the mathematical simplicity necessary to manipulate the governing equations conveniently, and despite a few deficiencies that will be pointed out, it seems to be a step in the right direction. In terms of compression, μ , the power-law ψ translates to a Grüneisen function of the form $\Gamma = \Gamma_0/(1+\mu)^{1-x}$.

Figure 2 shows the same TFD results as presented previously, except that several contours of a power-law $\psi(V)$ are superimposed on the graph, rather than the linear contours of Figure 1. At first glance, the power-law $\psi(V)$ might seem to offer only minimal benefit over the linearized form. Both forms cross over, rather than asymptote, to the TFD curves. Also, the power-law curves, though reducing to a value of zero, as is required, do so with an infinite limiting slope, so that the limiting value of Γ is not positive, but remains zero. On the positive side, however,




Figure 2. Limiting ψ values for several metals (solid lines), obtained by inserting TFD cold-curve values into equation of state of Segletes. Superimposed (dashed lines) are limiting ψ values associated with the power-law $\psi(V)$ assumption.

the curve corresponding to an exponent of 0.8 does blend nicely into the TFD curves. And of the nine metals examined by Segletes [15,16], seven had values for $\Gamma_0\psi'$ (corresponding roughly to exponent x) in the 0.75 to 0.88 range, where the power law fit approximates the TFD asymptote very well.

As far as actual cold-compression data, the power law and the linear assumption for $\psi(V)$ are nearly identical for $\Gamma_0\psi'$ values of 0.8 over relative volumes from unity down to 0.5. In this region, the power law provides a slightly more concave-upward curvature to the cold curve, which can be mitigated by choosing a value of exponent x , slightly below the fitted value of $\Gamma_0\psi'$ (e.g., whereas $\Gamma_0\psi'=0.76$ fits stainless steel, a value of $x=0.72$ fits comparably well). Over the range of available cold-compression data [10,21,22], the power-law and linear $\psi(V)$ formulations can be made virtually indistinguishable with appropriate selection of x , both resulting in excellent fits to the data.

On the expansion end of the curve, the power-law $\psi(V)$ is seen to provide an improved correlation to data. At high values of anharmonicity (~ 9), the linear model was able to match the universal cold-curve (UCC) fit of Rose *et al.* [10] with a value of $\Gamma_0\psi'$ approaching unity. The power law does equally well here, since for an exponent approaching unity, the linear and power forms are identical. However, for low anharmonicities (~ 3), no single value of $\Gamma_0\psi'$ could produce a match to the UCC model [15,16], but instead required a slope that was initially around 0.8, reducing to 0.55 at the larger expansions. Figure 3 compares the lattice potential energy predicted by the UCC model of Rose to that using the linear- ψ approximation. In this graph, the abscissa, a , represents the nondimensional, relative lattice spacing employed by Rose *et al.* [10].

By contrast, the power law $\psi(V)$ is able to match the UCC model closely with a single value of exponent x for a given anharmonicity. The value of the exponent x , which will provide a match to the UCC model, is given approximately by




Figure 3. Lattice binding energy as a function of nondimensionalized lattice spacing for a material. Dark line is UCC model of Rose et al. [10] Dashed lines are for model of Segletes [15,16], with linear ψ assumption, for two particular values of $\Gamma_0 \psi'$ and an anharmonicity of 3.

$$x = \frac{2}{3} + \frac{1}{3} \cdot (\eta/10) , \quad (8)$$

where η is the value of anharmonicity, as defined by Rose *et al.* [10]. The magnitude of anharmonicity provides a metric on the deviation of an actual crystal's behavior from the harmonic idealization, in which the binding force of the atomic lattice would be proportional to the atom's displacement from the rest position. It is later shown that Segletes' model [15,16] approximates the harmonic solid described by Dugdale and MacDonald [5] when the value of exponent x is selected as $2/3$, in accordance with the lower limit of eqn. (8), as $\eta \rightarrow 0$. Figure 4 compares the lattice binding energy predicted by the UCC model to that of the current model, when a power-law $\psi(V)$ is employed, the exponent being selected in accordance with eqn. (8). Though not labeled, the dark curve represents the UCC model, while the other five, essentially overlapping, curves are for the current model with anharmonicities of 2, 4, 6, 8, and 10.

4. GRÜNEISEN MODELS

Certain mathematical consequences of a power-law $\psi(V)$, eqn. (7), which are subsequently used, are easily derived and are simply stated as follows:

$$(\Gamma_0 \psi')_{V_0} = x ; \quad (9)$$

$$\psi' = x \cdot (\psi/V) ; \quad (10)$$

$$\psi' - n \cdot (\psi/V) = (x - n) \cdot (\psi/V) ; \text{ and} \quad (11)$$

$$\psi [\psi'' - n \cdot (\psi/V)'] = (x - n)(x - 1) \cdot (\psi/V)^2 . \quad (12)$$

We now intend to show the primary result of this paper—namely, that three historical Grüneisen formulations (those of Slater [4], Dugdale and MacDonald [5], and the free-volume




Figure 4. Lattice binding energy as a function of nondimensionalized lattice spacing for a material. Dark line is UCC model of Rose et al. [10]. Dashed lines (essentially coincident) are for model of Segletes [15,16], with power-law $\psi(V)$ assumption, for anharmonicity values of 2, 4, 6, 8, and 10.

theory [6]) may be recovered through manipulation of the current model, if the material is idealized and higher-order terms are neglected. Start with eqn. (4) and multiply by a power of specific volume, V^n , where n is, at this point, still an arbitrary constant:

$$(p_c V^n) = \frac{E_b K^2 V^n}{\psi} (\Theta/\Theta_0)^K \ln(\Theta/\Theta_0) . \quad (13)$$

The first and second derivatives of this equation may be obtained in a tedious but straightforward manner as:

$$(p_c V^n)' = -\frac{E_b K^2 V^n}{\psi^2} (\Theta/\Theta_0)^K \{ [K + \psi' - n(\psi/V)] \ln(\Theta/\Theta_0) + 1 \} \quad (14)$$

and

$$(p_c V^n)'' = \frac{E_b K^2 V^n}{\psi^3} (\Theta/\Theta_0)^K \left\{ [K + 2\psi' - n(\psi/V)] \{ [K + \psi' - n(\psi/V)] \ln(\Theta/\Theta_0) + 1 \} + \right. \\ \left. [K + \psi' - n(\psi/V)] - \psi[\psi'' - n(\psi/V)'] \ln(\Theta/\Theta_0) \right\} \quad (15)$$

Take eqn. (15) multiplied by $(-\psi)$ and divide by eqn. (14) to obtain:

$$-\psi \frac{(p_c V^n)''}{(p_c V^n)'} = 2K + 3\psi' - 2n(\psi/V) - \frac{\{ [K + \psi' - n(\psi/V)]^2 + \psi[\psi'' - n(\psi/V)'] \} \ln(\Theta/\Theta_0)}{1 + [K + \psi' - n(\psi/V)] \ln(\Theta/\Theta_0)} . \quad (16)$$

Eqns. (10–12) may be substituted into this expression to eliminate ψ' , the left hand ψ may be broken out as V/Γ , and the equation may be algebraically manipulated to give

$$-\frac{3x-2n}{2} - \frac{V}{2} \frac{(p_c V^n)''}{(p_c V^n)'} = \Gamma \times \left(K - \frac{1}{2} \frac{\{[K+(x-n)(\psi/V)]^2 + (x-n)(x-1)(\psi/V)^2\} \ln(\Theta/\Theta_0)}{1 + [K+(x-n)(\psi/V)] \ln(\Theta/\Theta_0)} \right) . \quad (17)$$

The large term in parentheses at the end of this equation takes on the value K at ambient conditions and diminishes with compression as the logarithm terms exert their influence. The material parameter K , for materials studied by Segletes [15,16], has generally been close to the idealized value of unity [whereupon $(C_0/\Gamma_0)^2 = E_b$]. For the sake of discussion, therefore, consider the large term in parentheses as unity, as an approximation to the situation near ambient volume [$\ln(\Theta/\Theta_0) \approx 0$] for an idealized material ($K \approx 1$). Eqn. (17) becomes

$$\Gamma = -\frac{3x-2n}{2} - \frac{V}{2} \frac{(p_c V^n)''}{(p_c V^n)'} . \quad (18)$$

In this equation, x , which denotes the power of $\psi(V)$, is a material parameter. If we select the value of parameter n , which has been arbitrary to this point, to be related to x in the following way:

$$n = 3x - 4/3 , \quad (19)$$

then x may be eliminated from eqn. (18) to yield

$$\Gamma = -\frac{4-3n}{6} - \frac{V}{2} \frac{(p_c V^n)''}{(p_c V^n)'} . \quad (20)$$

Eqn. (20) is precisely the generalized result presented by Vaschenko and Zubarev [6] for the

Grüneisen function. In this equation, if $n=0$ (*i.e.*, when $x=4/9$), Slater's [4] result is obtained. If $n=2/3$ (*i.e.*, when $x=2/3$), then the result of Dugdale and MacDonald [5] is recovered. Finally, for the case where $n=4/3$ (*i.e.*, when $x=8/9$), the free-volume theory [6] expression follows. What this result tells us is that any one of the three historical Grüneisen models may be nominally applicable, depending on the properties of the material of interest. In the case of those metals already studied by Segletes [15,16], values for $\Gamma_0\psi'$, which correspond to exponent x at ambient conditions [via eqn. (9)], fell as low as 0.43 ($\approx 4/9$) for molybdenum and as high as 0.88 ($\approx 8/9$) for rubidium, with the vast majority of materials in the 0.75–0.85 range.

5. NONIDEAL EFFECTS

Let us now consider the practical influence of the large term in parentheses in eqn. (17), idealized as unity in the previous section. The leading K term in the braces affects the ambient value of the Grüneisen parameter, while the remaining term involving logarithms governs the rate at which the Grüneisen function changes with volume. If Segletes' equation of state is accepted, then the fact that the large term in parentheses diminishes with volume indicates that all of the historical Grüneisen formulations (Slater, Dugdale-MacDonald, and free-volume theory) will tend to overestimate the rate of change of the Grüneisen function with compression when using a cold-compression curve as the baseline.

Whereas the historical Grüneisen models are based on various theories of lattice vibration, the model of Segletes [15,16], in contrast, is shown to fit actual cold and Hugoniot data well to several megabars of pressure. Thus, if one accepts the validity of the Grüneisen assumption [$\Gamma = f(V)$], then, over the compression range of actual thermodynamic data to which Segletes' model fits well, one must accept as more accurate the mildly varying Γ of that model to the more widely varying estimates produced by the theories of Slater, Dugdale-MacDonald and/or the free-volume theory.

To see how the models compare, Figures 5–7 depict the Grüneisen functional behavior for a hypothetical material with parameter $K=1$ and $\Gamma_0=2$. These three figures depict four curves




Figure 5. Grüneisen function versus relative volume for hypothetical material with $\Gamma_0=2$ and $K=1$, using power-law $\psi(V)$, with $x=4/9$. Predictions using models of Slater [4], Dugdale and MacDonald [5], and the free-volume theory [6] are shown for comparison. Note that ambient value associated with power-law $\psi(V)$ matches that of Slater.




Figure 6. Grüneisen function versus relative volume for hypothetical material with $\Gamma_0=2$ and $K=1$, using power-law $\psi(V)$, with $x=2/3$. Predictions using models of Slater [4], Dugdale and MacDonald [5], and the free-volume theory [6] are shown for comparison. Note that ambient value associated with power-law $\psi(V)$ matches that of Dugdale and MacDonald.




Figure 7. Grüneisen function versus relative volume for hypothetical material with $\Gamma_0=2$ and $K=1$, using power-law $\psi(V)$, with $x=8/9$. Predictions using models of Slater [4], Dugdale and MacDonald [5], and the free-volume theory [6] are shown for comparison. Note that ambient value associated with power-law $\psi(V)$ matches that of the free-volume theory.

each. In each graph, there is a Grüneisen curve corresponding to the power-law $\psi(V)$, with exponent x equal to $4/9$, $2/3$, and $8/9$ respectively. The resulting cold curve from the current model is used to show what the models of Slater, Dugdale-MacDonald, and the free-volume theory would predict for the behavior of the Grüneisen function, depicted in each of the figures by curves labeled S, D-M, and FVT, respectively. Per eqn. (17), with K equal to unity, the ambient values for the current theory match the value of Slater when $x=4/9$, that of Dugdale and MacDonald when $x=2/3$, and that of the free-volume theory when $x=8/9$.

To see a comparison of the other models to that of Segletes, for an actual material, we consider the case of stainless steel, because of the availability of good cold-curve data out to 4 Mbar. Figure 8 shows the cold curve and Hugoniot for the steel. The data points are the same as those originally analyzed by Segletes [15,16]. However, unlike the earlier work, in which a linear $\psi(V)$ function was fit to the data with a slope of 0.76, the cold curve is fit on this occasion with a power law, with an exponent, x , of 0.72. The Hugoniot fit is excellent as far as data are available (out to 2 Mbar). If the Grüneisen assumption is accepted, then a power law exponent of 0.72 must provide an accurate reflection of the Grüneisen function down to a relative volume of 0.68 (where Hugoniot data stop), and most likely provides an accurate reflection of the function down to a relative volume of 0.55 (where cold data stop). Figure 9 shows the Grüneisen function corresponding to this fit with the solid curve. Overlaid on the figure are the results of the models of Slater, Dugdale and MacDonald, and the free-volume theory, which are derived from the curvature of the stainless steel cold-curve fit. As pointed out previously, the other theories all show a Grüneisen function that decreases more rapidly in compression than the current model and data suggest.

Of course, at very high compressions and temperatures, electronic and non-Grüneisen thermal effects will come into play, and so even if a simple power law for $\psi(V)$ might blend into the TFD cold curve, it will likely fail to capture the high-temperature thermal effects properly. For example, the shock Hugoniot of most materials asymptotes at a V/V_0 value of around 0.2. Such an asymptote corresponds to a relative compression, μ , of 4. Segletes [9] proved that the asymptotic value of the Grüneisen parameter on the Hugoniot cannot exceed (and, in fact, must




Figure 8. Pressure-volume curves for stainless steel. Cold data to 4 Mbar shown with filled symbols. Hugoniot data to 2 Mbar shown with open symbols. Curves represent cold-compression and shock-Hugoniot curves with $\Gamma_0=1.81$ and power-law $\psi(V)$ exponent x , equal to 0.72.




Figure 9. Grüneisen function versus relative volume for stainless steel with $\Gamma_0=1.81$, using power-law $\psi(V)$, with $x=0.72$. Predictions using models of Slater [4], Dugdale and MacDonald [5], and the free-volume theory [6] are shown for comparison.

take on) a value of $2/\mu_{asym}$, which in this case, gives a value of 0.5. If the ambient value of the Grüneisen parameter were a typical value of $\Gamma_0=2$, then this asymptotic shock limit would possess a ψ/ψ_0 value of 0.8 at a V/V_0 value of 0.2. A quick look at the power-law curves of Figure 2 reveals that power-law $\psi(V)$ functions with exponents between 0.4 and 1.0 will not reach the point (0.2, 0.8). Thus, it would seem that the only way the Hugoniot can get to the point (0.2, 0.8) while the cold curve asymptotes to the TFD curves is if ψ is temperature dependent.

There is some reason to suspect such temperature-dependent behavior, by looking, for example, at the aluminum Hugoniot fit of Segletes [15,16]. When using the known ambient Grüneisen value (Segletes used 2.39) with the current model, the Hugoniot prediction was quite poor. But by using an ambient value of half that amount, which doubles the value of ψ , the aluminum Hugoniot and cold curve were fit with precision to 9 Mbar ($V/V_0 = 0.4$). One might be led to conclude that ψ is, indeed, temperature dependent and that, in the case of aluminum, a dependence occurs at relatively low temperatures. Such a thermal dependency would be able to explain how the Hugoniot can achieve relatively large asymptotic values of ψ/ψ_0 , while, at the same time, the cold-curve value diminishes below this level. A significant thermal dependency of the Grüneisen function for aluminum has been reported by Grodzka [1]. In particular, he cites experimental work with shocked aluminum foam that shows the ambient-volume aluminum Grüneisen parameter to decrease from a cold value of 2.5 to a value below 1.4 at 6500 J/g of specific internal energy. Using a value of $3R/W$ to approximate the specific heat over this range (where R is the universal constant, and W is the atomic weight of aluminum), 6500 J/g corresponds to a temperature of approximately 7000 K, and would result from a moderate-strength shock in the 1.5 Mbar range.

As a final note, another way in which Segletes' model and those of Slater, Dugdale and MacDonald, and the free-volume theory may be contrasted is accomplished by rearranging eqn. (20) as

$$\left[2 + \frac{4-3n}{3} (\psi/V) \right] \psi (p_c V^n)' + \psi^2 (p_c V^n)'' = 0 \quad . \quad (21)$$

As before, the value of n determines which of the three older models is being discussed. This equation is first-order in $(p_c V^n)'$. By comparison, the current model, with a power-law $\psi(V)$ function, satisfies the following identity:

$$K^2 (p_c V^x) + [2K + x(\psi/V)] \psi (p_c V^x)' + \psi^2 (p_c V^x)'' = 0 \quad , \quad (22)$$

which is second-order in $p_c V^x$. These two equations are obviously different, in that eqn. (21) contains only derivatives of $p_c V^n$, while eqn. (22) involves both $p_c V^x$ and its derivatives. However, there is also a great deal of similarity in that not only are both equations hyperbolic, but for the idealized, harmonic case of $K = 1$ and $x = n = 2/3$, eqns. (21) and (22) differ only by the first term of eqn. (22).

If eqn. (19) is used to convert eqn. (21) from n -based to x -based (to consider cases when $n \neq x$), it can be shown (for $K=1$) that the transformed eqn. (21) also differs from eqn. (22) only in the first term of eqn. (22), regardless of the value of x . It is for this reason that at ambient conditions, when p_c [and thus the first term of eqn. (22)] is zero, the value of Γ_0 from Segletes' model matches the older theories as a function of x , respectively. We can thus think of the older theories as each being applicable for a particular class of material (defined by material parameter x), but at the same time neglecting the $p_c V^x$ term necessary to capture the empirical data correctly.

6. CONCLUSIONS

In this report, the recently proposed equation of state of Segletes [15,16] has been examined for compatibility with prior theory. In the original work, an excellent match to available data and first-principles computations was achieved with the use of an assumed-linear expression for the $\psi(V)$ function, defined as V/Γ . In the current work, the use of a power law for $\psi(V)$ was examined in lieu of the linear relationship.

A number of positive outcomes resulted with the use of this power law. First, the low-volume limit for $\psi(V)$ approaches zero, which was shown to be desirable in order to have the current theory blend smoothly into Thomas-Fermi-Dirac cold-compression theory. Secondly, over the range of available cold-compression data, the linear and power-law fits can be made virtually indistinguishable, both providing excellent fits to the data. Finally, the binding energy function using a power-law $\psi(V)$ assumption was able to reproduce the fit of Rose *et al.* [10] better, especially in the area of lattice expansion. In this regard, an expression given by eqn. (8) shows a simple relation between material anharmonicity and the fitted parameter of the current model, in order to match the results of Rose *et al.* closely.

The primary result of the paper has been in showing how Segletes' model with a power-law $\psi(V)$, for the case of an idealized material, ignoring higher-order terms, is able to reproduce three historical Grüneisen function models, depending on the value of the fitted material parameter in Segletes' model. In particular, when the model parameter, which relates to the decrease of the Grüneisen function with compression, takes on a value of $4/9$, the result of Slater [4] is obtained. When the parameter is taken as $2/3$, the model of Dugdale and MacDonald [5] is recovered. Finally, if the model parameter takes the value of $8/9$, the free-volume theory [6] expression follows.

The paper then has shown how Segletes' model differs from the historical Grüneisen models, if the higher-order terms are retained. It becomes apparent that the historical models of the Grüneisen-function predict a more rapid decrease of the Grüneisen function with compression than does the current model. Some speculations have been put forward here on the possibility of a temperature-dependent ψ function, which would, by definition, violate the Grüneisen hypothesis. Not only would this possibility help to explain some seeming-incompatibilities between the behaviors of the high-compression cold curve and the asymptotic Hugoniot, but a temperature-dependent ψ could also explain the otherwise anomalous behavior for aluminum cited by Segletes [15,16] in the relative volume range of 0.85 to unity. Finally, the older Grüneisen models and Segletes' model have been mathematically expressed in a different form, which clearly shows the latter's distinction from the others. In the case of the comparison

between an idealized, harmonic material in the current model to the model of Dugdale and MacDonald, the distinction originates from a single $pV^{2/3}$ term, which represents a higher-order departure from the earlier theories.

There are several future efforts in this area that would be of utility. From a position of theoretical interest, it would be useful to reconcile the current theory with the very-high-pressure, equation-of-state theories, in something more than an empirical blend. Barring this reconciliation, however, the current theory has still shown its applicability into the megabar regime with excellent results, and should be of utility to those modeling material deformation resulting from impact and conventional explosive events in the ordnance regime. Also, the area of non-Grüneisen (and/or phase change) effects seems an interesting and important area for further work. For many materials, the Grüneisen approach seems perfectly adequate over a large range of compressions and pressures. However, there do seem to be materials (aluminum has been mentioned in this paper) for which non-Grüneisen effects at moderate pressures might provide an adequate explanation.

7. REFERENCES

1. Grodzka, P.G. "Grüneisen Parameter Study." LMSC/HREC A784868, Lockheed Missile Space Company, Huntsville, AL, October, 1967.
2. Blackman, M. "The Specific Heat of Solids." In *Encyclopedia of Physics; Volume VII - Part 1: Crystal Physics I*. S. Flügge (ed.), Berlin: Springer-Verlag, pp. 325–382, 1955.
3. Barron, H.T.K. "On the Thermal Expansion of Solids at Low Temperatures." *Philosophical Magazine*, **40**, pp. 720–734, 1955.
4. Slater, J.C. *Introduction to Chemical Physics*. New York: McGraw Hill, 1939.
5. Dugdale, J.S., and D.K.C. McDonald. "The Thermal Expansion of Solids." *Physical Review*, **89** (4), pp. 832–834, 1953.
6. Vashchenko, V.Y., and V.N. Zubarev. "Concerning the Grüneisen Constant." *Soviet Physics—Solid State*, **5** (3), pp. 653–655, 1963.
7. Pastine, D.J. "Formulation of the Grüneisen Parameter for Monatomic Cubic Crystals." *Physical Review*, **138** (3A), pp. A767–A770, 1965.
8. Walsh, J.M., M.H. Rice, R.G. McQueen, and F.L. Yarger. "Shock-Wave Compressions of Twenty-Seven Metals. Equations of State of Metals." *Physical Review*, **108** (2), pp. 196–216, 1957.
9. Segletes, S.B. "Thermodynamic Stability of the Mie-Grüneisen Equation of State, and Its Relevance to Hydrocode Computations." *Journal of Applied Physics*, **70** (5), pp. 2489–2499, 1991. Erratum: **71** (2), p. 1074.
10. Rose, J.H., J.R. Smith, F. Guinea, and J. Ferrante. "Universal Features of the Equation of State of Metals." *Physical Review B*, **29** (6), pp. 2963–2969, 1984.
11. Vinet, P., J.R. Smith, J. Ferrante, and J.H. Rose. "Temperature Effects on the Universal Equation of State for Solids." *Physical Review B*, **35** (4), pp. 1945–1953, 1987.

12. Vinet, P., J.H. Rose, J. Ferrante, J.R. Smith. "Universal Features of the Equation of State of Solids." *Journal of Physics: Condensed Matter*, **1**, pp. 1941–1963, 1989.
13. Baonza, V.G., M. Cáceres, and J. Núñez. "Universal Compressibility Behavior of Dense Phases." *Physical Review B*, **51** (1), pp. 28–37, 1995.
14. Baonza, V.G., M. Taravillo, M. Cáceres, J. Núñez. "Universal Features of the Equation of State of Solids from a Pseudospinodal Hypothesis." *Physical Review B*, **53** (9), pp. 5252–5258, 1996.
15. Segletes, S.B. "An Equation of State for Metals." ARL-TR-1270, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, November, 1996.
16. Segletes, S.B. "An Equation of State for Metals." *Journal of Applied Physics*, submitted for review, 1996.
17. Segletes, S.B. "Further Examinations on the Thermodynamic Stability of the Mie-Grüneisen Equation of State." *Journal of Applied Physics*, **76** (8), pp. 4560–4566, 1994.
18. Segletes, S.B. "The Effect of Thermodynamic Constraints Upon the Mie-Grüneisen Equation of State." In *Constitutive Laws*, A.M. Rajendran and R.C. Batra (eds.), CIMNE: Barcelona, pp. 46–51, 1995.
19. Brillouin, L. *Wave Propagation in Periodic Structures*. New York: Dover, 1953. Originally published by New York: McGraw Hill, 1946.
20. Kerley, G.I. "User Manual for PANDA II: A Computer Code for Calculating Equations of State." SAND88-2291, Sandia National Laboratories, Albuquerque, NM, July, 1991.
21. Mao, H.K., P.M. Bell, J.W. Shaner, and D.J. Steinberg. "Specific Volume Measurements of Cu, Mo, Pd, and Ag and Calibration of the Ruby R₁ Fluorescence Pressure Gauge From 0.06 to 1 Mbar." *Journal of Applied Physics*, **49** (6), pp. 3276–3283, 1978.
22. Molodets, A.M. "Grüneisen Function and the Zero-Temperature Isotherm of Three Metals up to Pressures of 10 TPa." *JETP*, **80** (3), pp. 467–471, 1995.

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	DEFENSE TECHNICAL INFO CTR ATTN DTIC DDA 8725 JOHN J KINGMAN RD STE 0944 FT BELVOIR VA 22060-6218
1	HQDA DAMO FDQ ATTN DENNIS SCHMIDT 400 ARMY PENTAGON WASHINGTON DC 20310-0460
1	US MILITARY ACADEMY MATH SCI CTR OF EXCELLENCE DEPT OF MATHEMATICAL SCI ATTN MDN A MAJ DON ENGEN THAYER HALL WEST POINT NY 10996-1786
1	DIRECTOR US ARMY RESEARCH LAB ATTN AMSRL CS AL TP 2800 POWDER MILL RD ADELPHI MD 20783-1145
1	DIRECTOR US ARMY RESEARCH LAB ATTN AMSRL CS AL TA 2800 POWDER MILL RD ADELPHI MD 20783-1145
3	DIRECTOR US ARMY RESEARCH LAB ATTN AMSRL CILL 2800 POWDER MILL RD ADELPHI MD 20783-1145
<u>ABERDEEN PROVING GROUND</u>	
2	DIR USARL ATTN AMSRL CI LP (305)

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	US ARMY DUSA OPS RSCH ATTN DANIEL WILLARD 102 ARMY PENTAGON WASHINGTON DC 20310-0102	1	COMMANDER USA STRATEGIC DEFNS CMD ATTN CSSD H LL T CROWLES HUNTSVILLE AL 35807-3801
1	ARMY SCIENCE BD WASH DC ATTN RICHARD L HALEY 2501 DUXBURY PLACE ALEXANDRIA VA 22308	2	COMMANDER US ARMY MICOM ATTN AMSMI RD ST WF D LOVELACE M SCHEXNAYDER REDSTONE ARSENAL AL 35898-5250
1	ARMY SCIENCE BOARD ORNL HEALTH SCI RSCH DIV ATTN ANETTA P WATSON BLDG 45005 MS 6101 OAK RIDGE TN 37831-6101	1	MIS DEFNS & SPACE TECHNOLOGY ATTN CSSD SD T KENNETH H JORDAN PO BOX 1500 HUNTSVILLE AL 34807-3801
1	MIT LINCOLN LAB ARMY SCIENCE BOARD ATTN WADE M KORNEGAY 244 WOOD ST RM S2 139 LEXINGTON MA 02173	4	COMMANDER US ARMY BELVOIR RD&E CTR ATTN STRBE NAE B WESTLICH STRBE JMC T HANSHAW STRBE NAN S G BISHOP J WILLIAMS FORT BELVOIR VA 22060-5166
5	DEFENSE NUCLEAR AGENCY ATTN MAJ JAMES LYON CDR KENNETH W HUNTER TONY FREDERICKSON R JEFFREY LAWRENCE SPSP KIM KIBONG 6801 TELEGRAPH RD ALEXANDRIA VA 22310-3398	3	COMMANDER US ARMY RESEARCH OFFICE ATTN J CHANDRA K IYER J BAILEY PO BOX 12211 RESEARCH TRIANGLE PARK NC 27709-2211
3	COMMANDER US ARMY ARDEC ATTN AMSTA AR FSA E W P DUNN J PEARSON E BAKER PICATINNY ARSENAL NJ 07806-5000	1	NAVAL RESEARCH LABORATORY ATTN ANDREW E WILLIAMS CODE 6684 4555 OVERLOOK AVE SW WASHINGTON DC 20375
1	COMMANDER US ARMY ARDEC ATTN AMSTA AR CCH V M D NICOLICH PICATINNY ARSENAL NJ 07806-5000	1	NAVAL AIR WARFARE CTR ATTN STEPHEN A FINNEGAN BOX 1018 RIDGECREST CA 93556
1	COMMANDER US ARMY ARDEC ATTN E ANDRICOPOULOS PICATINNY ARSENAL NJ 07806-5000	3	COMMANDER NAVAL WEAPONS CENTER ATTN T T YEE CODE 3263 D THOMPSON CODE 3268 W J MCCARTER CODE 6214 CHINA LAKE CA 93555

NO. OF COPIES	ORGANIZATION
9	<p>COMMANDER NAVAL SURFACE WARFARE CTR DAHLGREN DIVISION ATTN C R GARRETT CODE G22 W HOLT CODE G22 CHARLES R ELLINGTON W WALLACE MORTON JR JOHN M NELSON WILLIAM J STROTHER D L DICKINSON CODE G24 L F WILLIAMS CODE G33 M J SILL CODE H11 17320 DAHLGREN RD DAHLGREN VA 22448-5000</p>
13	<p>COMMANDER NAVAL SURFACE WARFARE CTR ATTN D TASKER CODE 9220 W WILSON P C HUANG CODE G402 B A BAUDLER CODE R12 R H MOFFETT CODE R12 R GARRETT CODE R12 T L JUNGLING CODE R32 R DAMINITY CODE U43 J P MATRA P WALTER L MENSI K KIDDY F J ZERILLI 10901 NEW HAMPSHIRE AVE SILVER SPRING MD 20903-5000</p>
1	<p>DIRECTOR NAVAL CIVIL ENGRNG LAB ATTN J YOUNG CODE L56 PORT HUENEME CA 93043</p>
1	<p>NAVAL POST GRADUATE SCHOOL PHYSICS DEPARTMENT ATTN JOSEPH STERNBERG MONTEREY CA 93943</p>

NO. OF COPIES	ORGANIZATION
5	<p>AIR FORCE ARMAMENT LAB ATTN AFATL DLJW W COOK M NIXON AFATL DLJR J FOSTER AFATL MNW LT D LOREY R D GUBA EGLIN AFB FL 32542</p>
5	<p>WRIGHT LABS ATTN MNMW JOEL W HOUSE ARMAMENT DIRECTORATE STE 326 B1 RONALD D HUNT BRYAN MILLIGAN BRUCE C PATTERSON WADE H VAUGHT 101 W EGLIN BLVD EGLIN AFB FL 32542-6810</p>
2	<p>USAF PHILLIPS LABORATORY ATTN PL WSCD FIROOZ ALLAHDAI PV VTA DAVID SPENCER 3550 ABERDEEN AVE SE KIRTLAND AFB NM 87117-5776</p>
1	<p>USAF PHILLIPS LABORATORY VTSI ATTN ROBERT ROYBAL KIRTLAND AFB NM 87117-7345</p>
1	<p>AFTT ENC ATTN DAVID A FULK WRIGHT PATTERSON AFB OH 45433</p>
1	<p>US DEPT OF ENERGY IDAHO OPERATIONS OFFICE ATTN RONALD H JOHNSON 850 ENERGY DR IDAHO FALLS ID 83401-1563</p>

NO. OF COPIES	ORGANIZATION
44	DIRECTOR SANDIA NATL LABS ATTN E S HERTEL JR MS 0819 L N KMETYK E H BARSIS MS 031 ERIC W REECE MS 0307 DANIEL P KELLY MS 0307 L WEIRICK MS 0327 R TACHAU MS 0425 D LONGCOPE MS 0439 R REEDER D HAYES MS 0457 J ASAY MS 0458 W TEDESCHI MS 0482 J SCHULZE MS 0483 J SOUTHWARD PAUL A LONGMIRE MS 0560 T TRUCANO MS 0819 J MICHAEL MCGLAUN MS 0819 R BRANNON MS 0820 J ANG MS 0821 M BOSLOUGH MS 0821 L CHHABILDAS MS 0821 D CRAWFORD MS 0821 J DICK M FURNISH MS 0821 C HALL MS 0821 W REINHART MS 0821 P STANTON MS 0821 P TAYLOR ORG 1432 D KERNAN ORG 1433 C KONRAD K LANG M KIPP DIV 1533 A ROBINSON DIV 1533 P YARRINGTON DIV 1533 J MCGLAWA DIV 1541 M FORRESTAL DIV 1551 R GRAHAM DIV 1551 R LAFARGE DIV 1551 C HILLS DIV 1822 W J ANDRZEJEWSKI DIV 2512 D MARCHI DIV 2512 W VANDERMOLLEN ORG 2653 B LEVIN ORG 7816 R O NELLUMS DIV 9122 PO BOX 5800 ALBUQUERQUE NM 87185-0307

NO. OF COPIES	ORGANIZATION
3	DIRECTOR LLNL ATTN JOSEPH V REPA MS A133 MICHAEL O SCHNICK MS F607 EDWARD J CHAPYAK MS F664 PO BOX 1663 LOS ALAMOS NM 87545
33	DIRECTOR LLNL ATTN R E TIPTON L35 D BAUM L35 T MCABEE MS 35 M J MURPHY R PIERCE L122 R ROSINKY L122 O J ALFORD L122 D STEWART L122 T VIDLAK L122 B R BOWMAN L122 W DIXON L122 A C MITCHELL J A MORIARTY R A HEINLE N C HOLMES R PERRET L163 W SHOTTS L163 H KRUGER L178 G POMYKAL L178 M SHANNON G SIMONSON L180 A SPERO L180 W TAO L282 P URTIEW L282 A HOLT L290 J E REAUGH L290 W J NELLIS L299 D WOOD L352 D GAVEL L495 J HUNTER L495 E JOHANSSON L495 R M KUKLO L874 G W REPP PO BOX 808 LIVERMORE CA 94550

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
8	DIRECTOR LLNL ATTN DOUGLAS R FAUX L125 NORMAN W KLINO L125H ROBERT BARKER L159 MILTON FINGER L163 MICHAEL GERASSIMENKO L178 FRANK A HANDLER L182 STEPHEN G COCHRAN L389 BMDO ROBERT M HALL PO BOX 808 LIVERMORE CA 94551-0808

33	DIRECTOR LANL ATTN M LUCERO MS A105 D MANDELL K MARK J P RITCHIE MS B214 T14 R DINGUS MS B218 N KRIKORIAN MS B228 R KIRKPATRICK MS B229 R THURSTON MS B229 C T KLINGNER MS B294 R MILLER MS B294 S J MOSSO B SHAFER MS C931 G GISLER MS D436 C RAGAN MS D449 B LAUBSCHER MS D460 R WELLS MS F607 R KOPP MS F645 R STELLINGWERF MS F645 C WINGATE MS F645 T ADAMS MS F663 R GODWIN MS F663 K JACOBY MS F663 W SPARKS MS F663 J SHANER MS F670 G CANAVAN MS F675 R GREINER MS G740 J HILLS MS G770 B HOGAN MS G770 J BOLSTAD MS G787 J WALSH MS G787 R DAVIDSON MS K557 R HENNINGER MS K557 N6 T ROLLET MS K574 PO BOX 1663 LOS ALAMOS NM 87545
----	---

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
12	DIRECTOR LANL ATTN P HOWE MS P915 W DEAL MS P915 J KENNEDY MS P915 A ROACH MS P915 L SCHWALBE W HEMSING MS P940 E POGUE MS P940 J MCAFEE MS P950 D PAISLEY MS P950 L PICKLESIMER MS P950 R WARNES MS P950 S SHEFFIELD MS P952 PO BOX 1663 LOS ALAMOS NM 87545
3	ENERGETIC MATERIALS RSCH CTR/DOE NEW MEXICO INST OF MINING & TECH ATTN DAVID J CHAVEZ LARRY LIBERSKY FRED SANDSTROM CAMPUS STATION SOCORRO NM 87801
1	NASA LEWIS RESEARCH CENTER ATTN J FERRANTE CLEVELAND OH 44135
3	NASA JOHNSON SPACE CENTER ATTN ERIC CHRISTIANSEN JEANNE LEE CREWS FREDRICH HORZ MAIL CODE SN3 2101 NASA RD 1 HOUSTON TX 77058
1	APPLIED RESEARCH LAB ATTN JEFFREY A COOK 10000 BURNETT ROAD AUSTIN TX 78758
1	GM RESEARCH LABS ATTN J R SMITH WARREN MI 48090

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
5	JET PROPULSION LABORATORY ATTN ZDENEK SEKANINA PAUL WEISSMAN BOB WEST JAMES ZWISSLER MARC ADAMS IMPACT PHYSICS GROUP 4800 OAK GROVE DR PASADENA CA 91109
1	MAXWELL LABS S CUBED DIVISION ATTN GERALD A GURTMAN PO BOX 1620 LA JOLLA CA 92037
1	AMES LABORATORY IOWA STATE UNIVERSITY ATTN J H ROSE AMES IA 50011
1	CALIFORNIA ST UNIV NORTHRIDGE ATTN JON H SHIVELY 10343 4TH ST NW ALBUQUERQUE NM 87114
2	CALTECH ATTN ANDREW P INGERSOLL MS 170 25 THOMAS J AHRENS MS 252 21 1201 E CALIFORNIA BLVD PASADENA CA 91125
1	CALTECH ATTN GLENN ORTON MS 169 237 4800 OAK GROVE DR PASADENA CA 91007
1	DREXEL UNIVERSITY ATTN PHYSICS DEPT 32ND & CHESTNUT ST PHILADELPHIA PA 19104
1	GEORGIA INSTITUTE OF TECHNOLOGY COMPUTATIONAL MODELING CENTER ATTN S ATLURI ATLANTA GA 30332-0356

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
5	JOHNS HOPKINS UNIV APPLIED PHYSICS LAB ATTN TERRY R BETZER ALVIN R EATON RICHARD H KEITH DALE K PACE ROGER L WEST JOHNS HOPKINS ROAD LAUREL MD 20723
1	LOUISIANA STATE UNIVERSITY ATTN ROBERT W COURTER 948 WYLIE DR BATON ROUGE LA 70808
1	MIT DEPT OF EARTH ATMOS AND PLANETARY SCIENCES ATTN HEIDI B HAMMELL 54 316 CAMBRIDGE MA 02139
1	NC STATE UNIVERSITY ATTN YASUYUKI HORIE RALEIGH NC 27695-7908
1	PENNSYLVANIA STATE UNIVERSITY ATTN PHYSICS DEPT UNIVERSITY PARK PA 16802
5	SOUTHWEST RESEARCH INSTITUTE ATTN C ANDERSON D LITTLEFIELD S A MULLIN B COUR PALAIS J WALKER PO DRAWER 28510 SAN ANTONIO TX 78284
1	STANFORD UNIVERSITY ATTN BRIAN PETERSEN RAINS 16L 704 CAMPUS DR STANFORD CA 94305
1	TEXAS A&M UNIVERSITY PHYSICS DEPARTMENT ATTN DAN BRUTON COLLEGE STATION TX 77843-4242

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	UC DAVIS INST OF THEORETICAL DYNAMICS ATTN E G PUCKETT DAVIS CA 95616
1	UC SANTA BARBARA INSTITUTE FOR THEORETICAL PHYSICS ATTN F GUINEA SANTA BARBARA CA 93106
2	UNIV OF ALA HUNTSVILLE AEROPHYSICS RSCH CTR ATTN GARY HOUGH DAVID J LIQUORNIK PO BOX 999 HUNTSVILLE AL 35899
1	UNIV OF ALA HUNTSVILLE CIVIL ENGRNG DEPT ATTN WILLIAM P SCHONBERG HUNTSVILLE AL 35899
1	UNIV OF ALABAMA ATTN A EUGENE CARDEN 86 EASTERN HILLS COTTONDALE AL 35453
1	UNIVERSITY OF ARIZONA ATTN DAVID H LEVY TUCSON AZ 85721
1	UNIVERSITY OF CA BERKLEY MECHNL ENGRNING DEPT GRADUATE OFFICE ATTN KEZHUN LI BERKELEY CA 94720
1	UNIVERSITY OF CHICAGO DEPT OF THE GEOPHYSICAL SCIENCES ATTN G H MILLER 5734 S ELLIS AVE CHICAGO IL 60637
1	UNIVERSITY OF COLORADO ATTN T MACLAY CAMPUS BOX 431 NNT 341 BOULDER CO 80309

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
4	UNIVERSITY OF DELAWARE DEPT OF MECHANICAL ENGINEERING ATTN PROF J GILLESPIE DEAN R B PIPES PROF J VINSON PROF D WILKINS NEWARK DE 19716
1	UNIVERSITY OF MARYLAND ATTN PHYSICS DEPT (BLDG 082) COLLEGE PARK MD 20742
1	UNIVERSITY OF PUERTO RICO DEPT CHEMICAL ENGINEERING ATTN L A ESTEVEZ MAYAGUEZ PR 00681-5000
1	UNIVERSITY OF TEXAS DEPT OF MECHANICAL ENGINEERING ATTN ERIC P FAHRENTHOLD AUSTIN TX 78712
1	VIRGINIA POLYTECHNIC INSTITUTE COLLEGE OF ENGINEERING ATTN R BATRA BLACKSBURG VA 24061-0219
1	ADVANCED TECHNOLOGY INC ATTN J ADAMS PO BOX 125 DAHLGREN VA 22448-0125
2	AEROJET ELECTRO SYS CO ATTN WARHEAD SYSTEMS J CARLEONE S KEY PO BOX 296 AZUSA CA 91702
2	AEROJET ORDNANCE ATTN P WOLF G PADGETT 1100 BULLOCH BLVD SOCORRO NM 87801

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
3	ALLIANT TECHSYSTEMS INC ATTN T HOLMQUIST MN11 2720 R STRYK G R JOHNSON MN11 2925 600 SECOND ST NE HOPKINS MN 55343
1	ALME AND ASSOCIATES ATTN MARVIN L ALME 6219 BRIGHT PLUME COLUMBIA MD 21044-3790
1	APPLIED RESEARCH ASSOC INC ATTN JEROME D YATTEAU 5941 S MIDDLEFIELD RD SUITE 100 LITTLETON CO 80123
1	APPLIED RESEARCH ASSOC INC ATTN FRANK MAESTAS 4300 SAN MATEO BLVD SE ALBUQUERQUE NM 87110
1	BATTELLE ATTN ROBER M DUGAS 7501 S MEMORIAL PKWY SUITE 101 HUNTSVILLE AL 35802-2258
3	BATTELLE ATTN S GOLASKI R JAMESON TECHNICAL LIBRARY 505 KING AVE COLUMBUS OH 43201
3	BOEING AEROSPACE CO SHOCK PHYSICS & APPLIED MATH ENGINEERING TECHNOLOGY ATTN R HELZER T MURRAY J SHRADER PO BOX 3999 SEATTLE WA 98124
1	BOEING HOUSTON SPACE STN ATTN RUSSELL F GRAVES BOX 58747 HOUSTON TX 77258

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	BRIGS CO ATTN JOSEPH E BACKOFEN 2668 PETERSBOROUGH ST HERNDON VA 22071-2443
3	CALIFORNIA RSCH & TECHNOLOGY ATTN R BROWN R FRANZEN D ORPHAL 5117 JOHNSON DR PLEASANTON CA 94566
1	CALIFORNIA RSCH & TECHNOLOGY ATTN M MAJERUS PO BOX 2229 PRINCETON NJ 08543
1	COMPUTATIONAL MECHANICS CONSULTANTS ATTN J A ZUKAS PO BOX 11314 BALTIMORE MD 21239-0314
1	DEFENSE TECHNOLOGY INTERNATIONAL INC ATTN D E AYER THE STARK HOUSE 22 CONCORD ST NASHUA NH 03060
1	DESKIN RESEARCH GROUP INC ATTN EDWARD COLLINS 2270 AGNEW RD SANTA CLARA CA 95054
2	EI DUPONT DE NEMOURS & CO ATTN L MINOR B SCOTT SECURITY DIR LEGAL DEPARTMENT PO BOX 1635 WILMINGTON DE 19899
1	G E DUVALL 5814 NE 82ND COURT VANCOUVER WA 98662-5944

NO. OF COPIES	ORGANIZATION
3	DYNA EAST CORP ATTN P C CHOU R CICCARELLI W FLIS 3620 HORIZON DRIVE KING OF PRUSSIA PA 19406
3	DYNASEN ATTN JACQUES CHAREST MICHAEL CHAREST MARTIN LILLY 20 ARNOLD PL GOLETA CA 93117
1	ELORET INSTITUTE ATTN DAVID W BOGDANOFF MS 230 2 NASA AMES RESEARCH CENTER MOFFETT FIELD CA 94035
3	ENIG ASSOCIATES INC ATTN J ENIG D J PASTINE M COWPERTHWAIT SUITE 500 11120 NEW HAMPSHIRE AVE SILVER SPRING MD 20904-2633
1	EXPLOSIVE TECHNOLOGY ATTN M L KNAEBEL PO BOX KK FAIRFIELD CA 94533
1	GB TECH LOCKHEED ATTN JAY LAUGHMAN 2200 SPACE PARK SUITE 400 HOUSTON TX 77258
2	GB TECH LOCKHEED ATTN LUCILLE BORREGO C23C JOE FALCON JR C23C 2400 NASA ROAD 1 HOUSTON TX 77058
2	GENERAL RESEARCH CORP ATTN A CHARTERS T MENNA PO BOX 6770 SANTA BARBARA CA 93160-6770

NO. OF COPIES	ORGANIZATION
2	GRC INTERNATIONAL ATTN TIMOTHY M CUNNINGHAM WILLIAM M ISBELL 5383 HOLLISTER AVE SANTA BARBARA CA 93111
5	INST OF ADVANCED TECHNOLOGY UNIVERSITY OF TX AUSTIN ATTN STEPHEN J BLESS JAMES CAZAMIAS HARRY D FAIR THOMAS M KIEHNE NICK LYNCH 4030-2 W BRAKER LN AUSTIN TX 78759
1	KAMAN SCIENCES CORP ATTN DENNIS L JONES 2560 HUNTINGTON AVE SUITE 200 ALEXANDRIA VA 22303
8	KAMAN SCIENCES CORP ATTN J ELDER RICHARD P HENDERSON DAVID A PYLES FRANK R SAVAGE JAMES A SUMMERS JAMES S WILBECK TIMOTHY W MOORE THY YEM 600 BLVD S SUITE 208 HUNTSVILLE AL 35802
3	KAMAN SCIENCES CORP ATTN SHELDON JONES GARY L PADEREWSKI ROBERT G PONZINI 1500 GRDN OF THE GODS RD COLORADO SPRINGS CO 80907
4	KAMAN SCIENCES CORP ATTN NASIT ARI STEVE R DIEHL WILLIAM DOANE VERNON M SMITH PO BOX 7463 COLORADO SPRINGS CO 80933-7463

NO. OF
COPIES ORGANIZATION

1 D R KENNEDY & ASSOC INC
ATTN D KENNEDY
PO BOX 4003
MOUNTAIN VIEW CA 94040

1 KERLEY PUBLISHING SERVICES
ATTN G I KERLEY
PO BOX 13835
ALBUQUERQUE NM 87192-3835

2 KTECH CORPORATION
ATTN FRANK W DAVIES
LARRY M LEE
901 PENNSYLVANIA NE
ALBUQUERQUE NM 87110

1 LIVERMORE SOFTWARE TECH CORP
ATTN J O HALLQUIST
2876 WAVERLY WAY
LIVERMORE CA 94550

1 LOCKHEED ENGRNG & SPC SCIENCES
ATTN E CYKOWSKI MS B22
2400 NASA RD 1
HOUSTON TX 77058

1 LOCKHEED MARTIN MISSILE & SPACE
ATTN WILLIAM R EBERLE
PO BOX 070017
HUNTSVILLE AL 35807

3 LOCKHEED MARTIN MISSILE & SPACE
ATTN M A LEVIN ORG 81 06 BLDG 598
M R MCHENRY
T A NGO ORG 81 10 BLDG 157
111 LOCKHEED WAY
SUNNYVALE CA 94088

4 LOCKHEED MISSILE & SPACE CO
ATTN JOHN R ANDERSON
WILLIAM C KNUDSON
S KUSUMI 0 81 11 BLDG 157
J PHILLIPS 0 54 50
PO BOX 3504
SUNNYVALE CA 94088

NO. OF
COPIES ORGANIZATION

1 LOCKHEED MISSILE & SPACE CO
ATTN R HOFFMAN
SANTA CRUZ FACILITY
EMPIRE GRADE RD
SANTA CRUZ CA 95060

1 LOCKHEED NASA JSC
SPACE SCIENCE BRANCH
ATTN JAMES HYDE
BOX 58561 MC B22
HOUSTON TX 77258

1 LOCKHEED MARTIN AEROSPACE
ATTN D R BRAGG
PO BOX 5837 MP 109
ORLANDO FL 32855

1 MCDONNELL DOUGLAS
ASTRONAUTICS CO
ATTN B L COOPER
5301 BOLSA AVE
HUNTINGTON BEACH CA 92647

1 ORLANDO TECHNOLOGY INC
ATTN DANIEL A MATUSKA
PO BOX 855
SHALIMAR FL 32579

1 PHYSICAL SCIENCES INC
ATTN PETER NEBOLSINE
20 NEW ENGLAND BUS CTR
ANDOVER MA 01810

3 PHYSICS INTERNATIONAL
ATTN R FUNSTON
G FRAZIER
L GARNETT
PO BOX 5010
SAN LEANDRO CA 94577

1 RAYTHEON ELECTRONIC SYSTEMS
ATTN R KARPP
50 APPLE HILL DRIVE
TEWKSBURY MA 01876

1 ROCKWELL INTERNATIONAL
ROCKETDYNE DIVISION
ATTN J MOLDENHAUER
6633 CANOGA AVE HB 23
CANOGA PARK CA 91303

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	ROCKWELL INTERNATIONAL ROCKETDYNE DIVISION ATTN H LEIFER 16557 PARK LN CIRCLE LOS ANGELES CA 90049
1	ROCKWELL MISSILE SYS DIV ATTN T NEUHART 1800 SATELLITE BLVD DULUTH GA 30136
1	S CUBED ATTN R SEDGWICK PO BOX 1620 LA JOLLA CA 92038-1620
2	SAIC ATTN JAMES FURLONG GREGORY J STRAUCH 1710 GOODRIDGE DR MCLEAN VA 22102
1	SAIC ATTN MICHAEL W MCKAY 10260 CAMPUS POINT DR SAN DIEGO CA 92121
1	SHOCK TRANSIENTS INC ATTN DAVID DAVISON BOX 5357 HOPKINS MN 55343
2	SIMULATION & ENG CO INC ATTN ELSA I MULLINS STEVEN E MULLINS 8840 HWY 20 SUITE 200 N MADISON AL 35758
2	SOUTHERN RESEARCH INSTITUTE ATTN LINDSEY A DECKARD DONALD P SEGERS PO BOX 55305 BIRMINGHAM AL 35255-5305
3	SRI INTERNATIONAL ATTN JAMES D COLTON DR L SEAMAN DONALD A SHOCKLEY 333 RAVENSWOOD AVE

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
	MENLO PARK CA 94025
2	TELEDYNE BROWN ENGR ATTN JIM W BOOTH MARTIN B RICHARDSON PO BOX 070007 MS 50 HUNTSVILLE AL 35807-7007
1	ZERNOW TECHNICAL SVCS INC ATTN LOUIS ZERNOW 425 W BONITA AVE SUITE 208 SAN DIMAS CA 91773
	ABERDEEN PROVING GROUND
26	DIR, USARL ATTN: AMSRL-WM, I MAY AMSRL-WM-T, W F MORRISON AMSRL-WM-TA, W GILlich W BRUCHEY J DEHN G FILBEY W A GOOCH H W MEYER E J RAPACKI AMSRL-WM-TB, R FREY J STARKENBERG AMSRL-WM-TC, W S DE ROSSET T W BJERKE R COATES F GRACE K KIMSEY M LAMPSON D SCHEFFLER S SCHRAML B SORENSEN R SUMMERS W WALTERS AMSRL-WM-PB, A ZIELINSKI AMSRL-WM-PD, G GAZONAS AMSRL-WM-WD, A PRAKASH AMSRL-WM-MF, A RAJENDRAN

NO. OF
COPIES ORGANIZATION

13 DIR, USARL
 ATTN: AMSRL-WM-TD,
 A M DIETRICH
 K FRANK
 J HARRISON
 M RAFTENBERG
 G RANDERS-PEHRSON
 J SANTIAGO
 M SCHEIDLER
 S SCHOENFELD
 S SEGLETES (3 CP)
 J WALTER
 T WRIGHT

NO. OF COPIES	ORGANIZATION
1	ABTEILUNG FUER PHYSIKALISCHE CHEMIE MONTANUNIVERSITAET ATTN E KOENIGSBERGER A 8700 LEOBEN AUSTRIA
2	AWE ATTN MICHAEL GERMAN WAYNE HARRISON FOULNESS ESSEX SS3 9XE UNITED KINGDOM
1	BATTELLE INGENIEUTECHNIK GMBH DUESSELDORFFER STR 9 ESCHBORN D 65760 GERMANY
1	BHABHA ATOMIC RESEARCH CENTRE HIGH PRESSURE PHYSICS DIVISION ATTN N SURESH TROMBAY BOMBAY 400 085 INDIA
1	BULGARIAN ACADEMY OF SCIENCES SPACE RESEARCH INSTITUTE ATTN VALENTIN GOSPODINOV 1000 SOFIA PO BOX 799 BULGARIA
1	CANADIAN ARSENALS LTD ATTN P PELLETIER 5 MONTEE DES ARSENAUX VILLIE DE GRADEUR PQ J5Z2 CANADA
1	CEA ATTN ROGER CHERET CEDEX 15 313 33 RUE DE LA FEDERATION PARIS 75752 FRANCE
1	CEA CISI BRANCH ATTN PATRICK DAVID CENTRE DE SACLAY BP 28 GIF SUR YVETTE 91192 FRANCE

NO. OF COPIES	ORGANIZATION
1	CEA/CESTA ATTN ALAIN GEILLE BOX 2 LE BARP 33114 FRANCE
3	CENTRE D'ETUDES DE GRAMAT ATTN SOLVE GERARD CHRISTIAN LOUPIAS PASCALE OUTREBON GRAMAT 46500 FRANCE
2	CENTRE D'ETUDES DE LIMEIL-VALENTON ATTN CHRISTIAN AUSSOURD JEAN-CLAUDE BOZIER SAINT GEORGES CEDEX VILLENEUVE 94195 FRANCE
3	CENTRE D'ETUDES DE VAUJOURS ATTN PLOTARD JEAN-PAUL ERIC BOTTET TAT SIHN VONG BOITE POSTALE NO 7 COUNTRY 77181 FRANCE
1	CENTURY DYNAMICS LTD ATTN NIGEL FRANCIS 12 CITY BUSINESS CTR BRIGHTON RD HORSHAM WEST SUSSEX RH1354BA UNITED KINGDOM
1	CRC RESEARCH INST INC ATTN MASAHIDE KATAYAMA STRUCTURAL ENGINEERING DEPT 1 3 316 NAKASE MIHAMA KU CHIBA SHI 261 01 JAPAN
1	DAT ETBS CETAM ATTN CLAUDE ALTMAYER ROUTE DE GUERRY BOURGES 18015 FRANCE

NO. OF
COPIES ORGANIZATION

1 DEFENCE RESEARCH AGENCY
ATTN W A J CARSON
CHOBHAM LANE CHERTSEY
SURREY KT16 0EE
UNITED KINGDOM

1 DEFENCE RSCH ESTAB SUFFIELD
ATTN D MACKAY
RALSTON ALBERTA TOJ 2NO RALSTON
CANADA

1 DEFENCE RSCH ESTAB SUFFIELD
ATTN CHRIS WEICKERT
BOX 4000 MEDICINE HAT
ALBERTA T1A 8K6
CANADA

1 DEFENCE RSCH ESTAB VALCARTIER
ATTN N GASS
PO BOX 8800
COURCELETTE PQ GOA IRO
CANADA

4 DEPARTAMENTO DE QUIMICA FISICA
FACULTAD DE CIENCIAS QUIMICAS
UNIVERSIDAD COMPLUTENSE DE
MADRID
ATTN V G BAONZA
M TARAVILLO
M CACERAS
J NUNEZ
28040 MADRID
SPAIN

1 DYNAMIC RESEARCH AB
ATTN AKE PERSSON
PARADISGRAND 7
SODERTALJE S 151 36
SWEDEN

4 ERNST MACH INSTITUT
ATTN VOLKER HOHLER
E SCHMOLINSKE
E SCHNEIDER
K THOMA
ECKERSTRASSE 4
D-7800 FREIBURG I BR 791 4
GERMANY

NO. OF
COPIES ORGANIZATION

1 ESTEC CS
ATTN DOUGLAS CASWELL
BOX 200 NOORDWIJK
2200 AG
NETHERLANDS

1 EUROPEAN SPACE AGENCY
ATTN WALTER FLURY
ESOC 5
ROBT BOSCHT STRASSE
DARMSTADT 6100
GERMANY

2 EUROPEAN SPACE AGENCY ESTEC
ATTN LUCY BERTHOUD
MICHEL LAMBERT
POSTBUS BOX 299 NOORDWIJK
NL2200 AG
NETHERLANDS

3 FRENCH GERMAN RESEARCH INST
ATTN HARTMUTH F LEHR
ROLF HUNKLER
ERICH WOLLMANN
POSTFACH 1260
WEIL AM RHEIN D-79574
GERMANY

3 FRENCH GERMAN RESEARCH INST
ATTN HANS-JURGEN ERNST
FRANCIS JAMET
PASCALE LEHMANN
CEDEX 5 5 RUE DU GENERAL CASSAGNOU
SAINT LOUIS 68301
FRANCE

4 HIGH ENERGY DENSITY RESEARCH CTR
ATTN VLADIMIR E FORTOV
GENADII I KANEL
V A SKVORTSOV
O YU VOJOBIEV
IZHORSKAJA STR 13/19
MOSCOW 127412
RUSSIAN REPUBLIC

NO. OF
COPIES ORGANIZATION

5 IABG
ATTN H J RAATSCHEN
W SCHITTKE
F F SCHARPPF
M BORRMANN
H G DORSCH
EINSTEINSTRASSE 20
D 8012 OTTOBRUN B MUENCHEN
GERMANY

1 INSTITUTE FOR PROBLEMS OF STRENGTH
ATTN G STEPANOV
TIMIRYAZEVSKEY STR 2
252014 KIEV
UKRAINE

1 INSTITUTE OF CHEMICAL PHYSICS
ATTN A YU DOLGOBORODOV
KOSYGIN ST 4 V 334
MOSCOW

3 INSTITUTE OF CHEMICAL PHYSICS
RUSSIAN ACADEMY OF SCIENCES
ATTN A M MOLODETS
S V RAZORENOV
A V UTKIN
142432 CHERNOGOLOVKA
MOSCOW REGION
RUSSIAN REPUBLIC

2 IOFFE PHYSICO TECHNICAL INSTITUTE
DENSE PLASMA DYNAMICS
LABORATORY
ATTN EDWARD M DROBYSHEVSKI
A KOZHUSHKO
ST PETERSBURG 194021
RUSSIAN REPUBLIC

1 IPE RAS
ATTN A A BOGOMAZ
DVORTSOVAIA NAB 18
ST PETERSBURG
RUSSIAN REPUBLIC

1 ISL
ATTN CHANTERET PIERRE-YVES
F68301 SAINT-LOUIS
CEDEX 12 RUE DE L'INDUSTRIE
BP 301
FRANCE

NO. OF
COPIES ORGANIZATION

1 LABORATOIRE DE TECHNOLOGIE DES
SURFACES
ECOLE CENTRALE DE LYON
ATTN PASCAL VINET
BP 163
69131 ECULLY CEDEX
FRANCE

2 LAVRENTYEV INST. HYDRODYNAMICS
ATTN LEV A MERZHEVSKY
VICTOR V SILVESTROV
NOVOSIBIRSK 630090
RUSSIAN REPUBLIC

1 MOSCOW INST OF PHYSICS & TECH
ATTN S V UTYUZHNIKOV
DEPT OF COMPUTATIONAL MATHEMATICS
DOLGOPRUDNY 1471700
RUSSIAN REPUBLIC

1 NATL DEFENCE DENSITY RSCH CTR
ATTN JOHAN FORSS
FOA FOX 551
TUMBA S 14725
SWEDEN

3 NATL DEFENCE RESEARCH EST
ATTN LARS HOLMBERG
ULF LINDEBERG
LARS GUNNAR OLSSON
FOA BOX 551
TUMBA S 14725
SWEDEN

1 PML TNO
ATTN EDWARD VAN RIET
BOX 45
RIJSWIJK 2230AA
NETHERLANDS

1 PRB S A
ATTN M VANSNICK
AVENUE DE TERVUEREN 168 BTE 7
BRUSSELS B 1150
BELGIUM

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	PRINS MAURITS LABORATORY ATTN H J REITSMA TNO BOX 45 RIJSWIJK 2280AA NETHERLANDS	1	TU CHEMNITZ-ZWICKAU ATTN LOTHAR MEYER FAKULTAET FUER MASCHINENBAU U. VERFAHRENSTECHNIK SCHEFFELSTRASSE 110 09120 CHEMNITZ GERMANY
2	RAFAEL BALLISTICS CENTER ATTN EREZ DEKEL YEHUDA PARTOM PO BOX 2250 HAIFA 31021 ISRAEL	1	UK MINISTRY OF DEFENCE ATTN GRAHAM J CAMBRAY CBDE PORTON DOWN SALISBURY WITTSIRE SPR 0JQ UNITED KINGDOM
1	RESEARCH INSTITUTE OF MECHANICS NIZHNIY NOVGOROD STATE UNIVERSITY ATTN A SADYRIN P.R. GAYARINA 23 KORP 6 NIZHNIY NOVGOROD 603600 RUSSIAN REPUBLIC	1	UNIVERSIDAD DE CANTABRIA FACULTAD DE CIENCIAS DEPARTAMENTO DE FISICA APLICADA ATTN J AMOROS AVDA DE LOS CASTROS S/N SANTANDER SPAIN
1	ROYAL ARMAMENT R&D ESTAB ATTN I CULLIS FORT HALSTEAD SEVENOAKS KENT TN14 7BJ UNITED KINGDOM	1	UNIVERSIDAD DE OVIEDO FACULTAD DE QUIMICA DEPARTAMENTO DE QUIMICA FISICA Y ANALITICA ATTN E FRANCISCO AVENIDA JULIAN CLAVERIA S/N 33006 - OVIEDO SPAIN
1	SAMARA STATE AEROSPACE UNIV ATTN L G LUKASHEV SAMARA RUSSIAN REPUBLIC	1	UNIVERSITY OF GUELPH PHYSICS DEPT ATTN C G GRAY GUELPH ONTARIO N1G 2W1 CANADA
1	TECHNISCHE UNIVERSITAT MUENCHEN ATTN EDUARD B IGENBERGS RICHARD WAGNER STR 18 111 MUENCHEN 2 D8000 GERMANY	2	UNIVERSITY OF KENT UNIT FOR SPACE SCIENCES ATTN PHILIPPE GENTA PAUL RATCLIFF CANTERBURY KENT CT2 7NR UNITED KINGDOM
1	TOMSK BRANCH OF THE INSTITUTE FOR STRUCTURAL MACROKINETICS ATTN V GORELSKI 8 LENIN SQ GSP 18 TOMSK 634050 RUSSIAN REPUBLIC		

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project(0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE March 1997		3. REPORT TYPE AND DATES COVERED Final, Sep - Oct 96
4. TITLE AND SUBTITLE On Theories of the Grüneisen Parameter			5. FUNDING NUMBERS PR: 1L162618AH80	
6. AUTHOR(S) Steven B. Segletes and William P. Walters				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRL-WM-TD Aberdeen Proving Ground, MD 21005-5066			8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-1303	
9. SPONSORING/MONITORING AGENCY NAMES(S) AND ADDRESS(ES)			10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) A recently proposed equation of state is further examined for compatibility with prior theory. It is found, by adopting a more realistic functional relationship for one of the thermodynamic state variables and eliminating higher-order terms from the model, that three historical theories for determination of the Grüneisen function fall directly out of the recently proposed model. One is led to conclude that the newer model captures the essence of all of the older theories, each of which being applicable under an appropriate circumstance.				
14. SUBJECT TERMS equation of state, lattice frequency, Grüneisen, Debye temperature			15. NUMBER OF PAGES 47	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

INTENTIONALLY LEFT BLANK.

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number/Author ARL-TR-1303 (Segletes) Date of Report March 1997
2. Date Report Received _____
3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT
ADDRESS

Organization

Name

E-mail Name

Street or P.O. Box No.

City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD
ADDRESS

Organization

Name

Street or P.O. Box No.

City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)
(DO NOT STAPLE)

DEPARTMENT OF THE ARMY


OFFICIAL BUSINESS

BUSINESS REPLY MAIL

FIRST CLASS PERMIT NO 0001,APG,MD

POSTAGE WILL BE PAID BY ADDRESSEE

DIRECTOR
US ARMY RESEARCH LABORATORY
ATTN AMSRL WM TD
ABERDEEN PROVING GROUND MD 21005-5066



NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

